



# Elgiloy Specialty Metals – Strip Products

## Inconel® alloy 625

UNS N06625  
W. Nr 2.4856

### Applicable Specifications

Strip and Foil ASTM B443, AMS 5599, AMS 5869, ISO 6208, NACE MR0175/ISO 15156-3, NACE MR0103/ISO 17945

**Description:** Inconel® 625 is a Nickel-Chromium-Molybdenum-Columbium (Niobium) alloy with excellent oxidation resistance, corrosion resistance, and strength at high temperatures. Age-hardening treatments are not required to obtain the high strength properties of Alloy 625 due to the solid solution effects of molybdenum and columbium on the nickel-chromium matrix. 1625 is resistant to chloride-ion stress-corrosion cracking, pitting, and stress-corrosion cracking making it suitable for seawater applications. Inconel® 625 can operate from cryogenic temperatures up to 1800°F (980°C).

**Applications include:** Honeycomb, springs, seals, bellows, diaphragms, land-based turbine components, aircraft exhaust ducting, and heat exchangers.

**Industries supplied include:** Automotive, Marine, Chemical Processing, Power Generation, Nuclear and Aerospace.

### Nominal Composition

	C	Mn	Si	P	S	Cr	Mo	Nb	Co	Ti	Al	Fe	Ni
min						20.00	8.00	3.15					
max	0.10	0.50	0.50	0.015	0.015	23.00	10.00	4.15	1.00	0.40	0.40	5.00	Bal

### Physical Properties

	At 70°F	At 20°C
Density	0.305 lb/in <sup>3</sup>	8.44 g/cm <sup>3</sup>
Modulus of Elasticity (E)	30.1 x 10 <sup>3</sup> ksi	208 GPa
Modulus of Rigidity (G)	11.8 x 10 <sup>3</sup> ksi	81.2 GPa
Coefficient of Expansion	7.4 microinches/in.-°F (70-600°F)	13.3 μm/m-°C (20-538°C)
Electrical Resistivity	50.8 μ ohm.in	129 μ ohm.cm
Thermal Conductivity	68 Btu-in./ft. <sup>2</sup> hr.-°F	9.8 W/m-K

### Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	1925-2050°F (1050-1120°C)	120 – 150 ksi (830-1100 MPa)	-300°F to 1800°F (-184°C to 980°C)
Spring Temper		200 - 250 ksi (1380 - 1724 MPa)	-300°F to 700°F (-184°C to 370°C)

INCONEL® is a registered trademark of the Special Metals Corporation group of companies.

#### Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information:

Email: [stripinquiries@elgiloy.com](mailto:stripinquiries@elgiloy.com)  
Phone: 1-888-843-2350

Elgiloy Specialty Metals - Strip Products

1565 Fleetwood Dr.  
Elgin, IL 60123 USA

[www.elgiloy.com](http://www.elgiloy.com)

Rev Date: 11/1/2022