

## **Elgiloy Specialty Metals – Strip Products**

## Inconel<sup>®</sup> alloy 625

## UNS N06625 W. Nr 2.4856

## Applicable Specifications

Strip and Foil ASTM B443, AMS 5599, AMS 5869, ISO 6208, NACE MR0175/ISO 15156-3, NACE MR0103/ISO 17945

**Description:** Inconel<sup>®</sup> 625 is a Nickel-Chromium-Molybdenum-Columbium (Niobium) alloy with excellent oxidation resistance, corrosion resistance, and strength at high temperatures. Age-hardening treatments are not required to obtain the high strength properties of Alloy 625 due to the solid solution effects of molybdenum and columbium on the nickel-chromium matrix. I625 is resistant to chloride-ion stress-corrosion cracking, pitting, and stress-corrosion cracking making it suitable for seawater applications. Inconel<sup>®</sup> 625 can operate from cryogenic temperatures up to 1800°F (980°C).

**Applications include:** Honeycomb, springs, seals, bellows, diaphragms, land-based turbine components, aircraft exhaust ducting, and heat exchangers.

Industries supplied include: Automotive, Marine, Chemical Processing, Power Generation, Nuclear and Aerospace.

Nominal Composition													
	с	Mn	Si	Р	S	Cr	Мо	Nb	Со	Ti	AI	Fe	Ni
min						20.00	8.00	3.15					
max	0.10	0.50	0.50	0.015	0.015	23.00	10.00	4.15	1.00	0.40	0.40	5.00	Bal
Physical Properties													
				At 70°F					At 20°C				
Density				0.305 lb/in <sup>3</sup>					8.44 g/cm <sup>3</sup>				
Modulus of Elasticity (E)				30.1 x 10 <sup>3</sup> ksi					208 GPa				
Modulus of Rigidity (G)				11.8 x 10 <sup>3</sup> ksi					81.2 GPa				
Coefficient of Expansion				7.4 microinches/in°F (70-600°F)					13.3 μm/m-°C (20-538°C)				
Electrical Resistivity				50.8 μ ohm.in					129 μ ohm.cm				
Thermal Conductivity				68 Btu-in./ft. <sup>2</sup> hr°F					9.8 W/m-К				
Typical Mechanical Properties													
Condition Heat			Heat Tr	Treatment				Tensile Strength		Suggested Operating Conditions			
Annea	Annealed 1925			-2050°F (1050-1120°C)				120 – 150 ksi (830-1100 MPa)		-300°F to 1800°F (-184°C to 980°C)			
Spring Temper								200 - 250 (1380 - 17	-	-300°F to 700°F (-184°C to 370°C)			

INCONEL® is a registered trademark of the Special Metals Corporation group of companies.

Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information:	Elgiloy Specialty Metals - Strip Products				
Email: stripinquiries@elgiloy.com	1565 Fleetwood Dr.	www.elgiloy.com			
Phone: 1-888-843-2350	Elgin, IL 60123 USA				

Rev Date: 6/2/2021