

Elgiloy Specialty Metals – Wire Products

Hastelloy® B-3® alloy

UNS N10675 W. Nr 2.4600

Applicable Specifications

Wire & Bar

ASTM B335

Description: Hastelloy® B-3® alloy is a nickel-molybdenum alloy with increased structural and thermal stability compared to that of Hastelloy® B-2®. It has excellent resistance to pitting, corrosion, and stress corrosion cracking in high-purity acid environments. It has excellent resistance to hydrochloric acid at all concentrations and temperatures. The alloy can withstand most concentrations of sulfuric, acetic, formic, and phosphoric acids, as well as other nonoxidizing media. Hastelloy® B-3® can be cold worked to increase strength with limited effects on general corrosion resistance but is recommended to be re-annealed for optimum stress corrosion cracking resistance.

Applications include: Reaction vessels, Welding wire, Fittings, Rings, Springs

Industries supplied include: Chemical Processing

| Nominal Composition | | | | | | | | | | |
|---------------------|----------|----------|----------|-----------|----------|-----------|-------------|-----------|--|--|
| С | Mn | Si | S | P | Ni | Cr | Мо | Со | | |
| 0.01 max | 3.0 max | 0.10 max | 0.03 max | 0.030 max | 65.0 min | 1.0 - 3.0 | 27.0 - 32.0 | 3.0 max | | |
| Nb (Cb) | V | Al | Cu | Та | Ti | W | Zr | Fe | | |
| 0.20 max | 0.20 max | 0.50 max | 0.20 max | 0.20 max | 0.20 max | 3.0 max | 0.10 max | 1.0 - 3.0 | | |

Physical Properties

| | At 70°F | At 20°C | |
|---------------------------|----------------------------|-------------------------|--|
| Density | 0.333 lb/in ³ | 9.22 g/cm ³ | |
| Modulus of Elasticity (E) | 31.4 x 10 ³ ksi | 216 GPa | |
| Coefficient of Expansion | 6.5 μin/in-°F (70-1200°F) | 11.8 μm/m-°C (25-600°C) | |
| Electrical Resistivity | 53.8 μohm-in | 136.6 μohm-cm | |
| Thermal Conductivity | 78 Btu-in/ft²-hr-°F | 11.2 W/m-°C | |
| | | | |

Typical Mechanical Properties

| Condition | Heat Treatment | Tensile Strength | Suggested Operating Conditions | |
|---------------|-----------------|----------------------------|------------------------------------|--|
| Annealed | 1950°F (1066°C) | 120-150 ksi (827-1035 MPa) | -320°F to 1200°F (-200°C to 650°C) | |
| Spring Temper | None | 200 ksi min (1379 MPa) | Up to 750°F (400°C) | |

Hastelloy® B-3® and B-2® are registered trademarks of Haynes International, Inc.

Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to
 the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information
 contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information: Email: wireinquiries@elgiloy.com Phone: 1-847-695-1900 Elgiloy Specialty Metals – Wire Products 356 North Cross Street Sycamore, IL 60178 USA

www.elgiloy.com

Rev Date: 6/17/2020