



Elgiloy Specialty Metals – Wire Products

Hastelloy® alloy X

UNS N06002
W.Nr 2.4665

Applicable Specifications

Wire & Bar | AMS 5754, AMS 5798, DMD 0491, GE B21B111, ASTM B572

Description: HASTELLOY® alloy X is a nickel-chromium-iron-molybdenum alloy that possesses an exceptional combination of oxidation resistance, fabricability and high-temperature strength. Alloy X exhibits good ductility after prolonged exposure to high temperatures. HASTELLOY® X has excellent hot and cold formability and can be welded readily by a variety of techniques.

Applications include: Land-based Gas Turbine, High Temperature fixtures, Petrochemical Applications

Industries supplied include: Aerospace, Automotive, Industrial Heating, Chemical Processing

Nominal Composition

	C	Mn	Si	P	S	Cr	Co	Mo	W	Fe	Al	Ti	Ni
min	0.05					20.50	0.50	8.00	0.20	17.00			47 (bal)
max	0.15	1.00	1.00	0.040	0.030	23.00	2.50	10.00	1.00	20.00	0.50	0.15	

Physical Properties

	At 70°F	At 20°C
Density	0.297 lb/in ³	8.22 g/cm ³
Modulus of Elasticity (E)	29.8 x 10 ³ ksi	205 GPa
Modulus of Rigidity (G)	11.3 x 10 ³ ksi	77.6 GPa
Coefficient of Expansion	8.1 μin/in-°F (70-1000 °F)	14.5 μm/m-°C (20-538 °C)
Electrical Resistivity	45.4 μohm-in	17.87 μohm-cm
Thermal Conductivity	63 Btu-in./ft ² hr-°F	9.2 W/m-°C

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	Per Specifications	110-135 ksi	-300°F to 2200°F (-184°C to 1205°C)
Spring Temper	None	200 ksi min	-300°F to 2200°F (-184°C to 1205°C)

Hastelloy® is a registered trademark of Haynes International, Inc.

Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information:
Email: wireinquiries@elgiloy.com
Phone: 1-847-695-1900

Elgiloy Specialty Metals – Wire Products
356 North Cross Street
Sycamore, IL 60178 USA

www.elgiloy.com

Rev Date: 6/17/2020