



Elgiloy Specialty Metals – Wire Products

Haynes® alloy 188

**UNS R30188
W.Nr 2.4683**

Applicable Specifications

Wire & Bar AMS 5772, GE B50A712

Description: Haynes® Alloy 188 is a cobalt-nickel-chromium-tungsten alloy with excellent high temperature tensile strength, sulfidation, and oxidation resistance up to 1095°C (2000°F) for long term exposures. Haynes® Alloy 188 is not age hardenable but may be cold worked to achieve higher tensile and yield strength. Haynes® Alloy 188 responds well to conventional forming and welding techniques.

Applications include: High Temperature and Corrosion Resistant Applications

Industries supplied include: Military and Commercial Aerospace, Chemical Processing, and Land-Based Gas Turbines

Nominal Composition

	C	Mn	P	S	Si	Cr	Ni	Co	B	Fe	W	La
Min	0.05				0.20	20.0	20.0	39 (bal)			13.0	0.03
Max	0.15	1.25	0.02	0.015	0.50	24.0	24.0		0.015	3.00	16.0	0.12

Physical Properties

	At 70°F	At 20°C
Density	0.24 lb/in ³	8.98 g/cm ³
Modulus of Elasticity (E)	33.7 x 10 ³ ksi	232 GPa
Modulus of Rigidity (G)	13 x 10 ³ ksi	90 GPa
Coefficient of Expansion	9.1 μin/in/°F (75-1800°F)	16.5 μm/m-°C (25-1000°C)
Electrical Resistivity	39.6 μohm-in	101.0 μohm-cm
Thermal Conductivity	72 Btu-in/ft ² -hr-°F	10.4 W/m-°C

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2150 °F (1177 °C)	125 ksi min	-300°F to 2000°F (-185°C to 1095°C)
Spring Temper	None	200 ksi min	-300°F to 2000°F (-185°C to 1095°C)
Spring Temper + Aged			

Haynes® is a registered trademark of Haynes International, Inc.

Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information:
Email: wireinquiries@elgiloy.com
Phone: 1-847-695-1900

Elgiloy Specialty Metals – Wire Products
356 North Cross Street
Sycamore, IL 60178 USA

www.elgiloy.com

Rev Date: 6/17/2020