

Elgiloy Specialty Metals – Wire Products

Haynes® Alloy 214

UNS N07214 W.Nr 2.4646

Applicable Specifications

Wire & Bar

PS-6104, PWA 1130

Description: Haynes® Alloy 214 is a nickel-chromium-aluminum-iron alloy with excellent high temperature corrosion and oxidation resistance at and above 955°C (1750°F). Haynes® Alloy 214 is sold in the solution heat treated condition and is best suited for high temperature, low stress environments. At temperatures above 1750°F, an Al_2O_3 type oxide scale develops, providing excellent resistance to carburization, nitriding and corrosion in chlorine-bearing oxidizing environments. H214 exhibits good forming and welding characteristics, provided that extended time at intermediate agehardening temperatures is avoided.

Applications include: High temperature mesh/fixtures, refractory anchors, static oxidation-limited parts, high temperature chlorine-contaminated applications

Industries supplied include: Aerospace, Automotive, Industrial Heating, Medical Waste Disposal, and Land-Based Gas Turbines.

| Nominal Composition | | | | | | | | | | | | | | |
|---------------------|------|------|------|-------|------|------|------|------|------|------|-------|------|------|--------|
| | С | Mn | Si | S | Cr | Со | Мо | W | Ti | Al | В | Fe | Υ | Ni |
| min | | | | | 15.0 | | | | | 4.00 | | 2.00 | .002 | 75 Bal |
| max | 0.15 | 1.00 | 0.50 | 0.015 | 17.0 | 2.00 | 1.00 | 1.00 | 0.50 | 5.00 | 0.015 | 6.00 | .040 | |

Physical Properties

| | At 70°F | At 20°C |
|---------------------------|----------------------------|--------------------------|
| Density | 0.291 lb/in³ | 08.05 g/cm ³ |
| Modulus of Elasticity (E) | 31.6 x 10³ ksi | 218 GPa |
| Coefficient of Expansion | 11.1 μin/in-°F (70-2000°F) | 20.2 μm/m-°C (25-1100°C) |
| Electrical Resistivity | 53.5 μohm-in | 135.9 μohm-cm |
| Thermal Conductivity | 83 Btu-in/ft²-hr-°F | 12.0 W/m-°C |
| | | |

Typical Mechanical Properties

| Condition | Heat Treatment | Tensile Strength | Suggested Operating Conditions | | |
|-----------|---------------------------|----------------------------|-------------------------------------|--|--|
| Annealed | 1950-2050°F (1066-1121°C) | 130-150 ksi (895-1035 MPa) | -330°F to 2400°F (-200°C to 1315°C) | | |
| | | | | | |
| | | | | | |

Haynes® is a registered trademark of Haynes International, Inc.

For further information: Email: wireinquiries@elgiloy.com Phone: 1-847-695-1900 Elgiloy Specialty Metals – Wire Products 356 North Cross Street Sycamore, IL 60178 USA

www.elgiloy.com

Rev Date: 8/28/2020