

Elgiloy Specialty Metals – Wire Products

Haynes[®] 230[®] alloy

UNS N06230 W. Nr 2.4733

Applicable Specifications

Wire & Bar AMS 5878 & ASTM B435 (chemistry only)

Description: Haynes[®] 230[®] alloy is a nickel-chromium-tungsten-molybdenum alloy which combines excellent high temperature strength and oxidation resistance up to 2100°F with superior long-term stability and good fabricability. It has lower thermal expansion characteristics than most high temperature alloys and resists grain coarsening with prolonged heat exposure. Haynes[®] 230[®] also exhibits excellent low cycle fatigue properties at high temperatures and is one of the most nitriding resistant materials available.

Applications include: Heat treatment baskets, Catalyst grid supports, Gas turbine components, Heat exchangers, Bellows, Wire mesh belts, Heat treating fixtures, Basket liners, Muffles/retorts, Dampers, Thermocouple sheathing, Flame shrouds

Industries supplied include: Industrial Heat Treating, Power Generation, Aerospace, Chemical Processing

Nominal Composition														
	С	Mn	Si	Р	S	В	Ni	Cr	Со	Мо	La	W	Al	Fe
min	0.05	0.30	0.25	-	-	-	Bal	20.00	-	1.00	0.005	13.00	-	-
max	0.15	1.00	0.75	0.030	0.015	0.015	-	24.00	5.00	3.00	0.05	15.00	0.50	3.00

Physical Properties

	At 70°F	At 20°C		
Density	0.324 lb/in ³	8.97 g/cm ³		
Modulus of Elasticity (E)	30.3 x 10 ³ ksi	209 GPa		
Modulus of Rigidity (G)	11.5 x 10 ³ ksi	79 GPa		
Coefficient of Expansion	8.9 μin/in-°F (70-1800°F)	16.1 μm/m-°C (25-1000°C)		
Electrical Resistivity	49.2 μohm-in	125.0 μohm-cm		
Thermal Conductivity	62 Btu-in/ft ² -hr-°F	8.9 W/m-°C		

Typical Mechanical Properties

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions
Annealed	2048-2246°F (1120-1230°C)	110-140 ksi (758-965 MPa)	Up to 2100°F (1150°C)

Haynes® 230® and MULTIMET® are registered trademarks of Haynes International, Inc.

Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information: Email: wireinquiries@elgiloy.com Phone: 1-847-695-1900 Elgiloy Specialty Metals – Wire Products 356 North Cross Street Sycamore, IL 60178 USA

www.elgiloy.com

Rev Date: 6/17/2020