

# **Elgiloy Specialty Metals – Wire Products**

## Haynes<sup>®</sup> 242<sup>®</sup> alloy

**UNS N10242** 

### **Applicable Specifications**

### Wire & Bar ASTM B434 (chemistry only)

**Description:** HAYNES<sup>®</sup> 242<sup>®</sup> alloy is an age-hardenable nickel-molybdenum chromium alloy which can be strengthened through an ordering reaction upon aging, while maintaining high ductility. The alloy's tensile and creep strength properties up to 1300°F (705°C) are considerably improved compared to solid solution strengthened alloys. The coefficient of thermal expansion for 242<sup>®</sup> alloy are also lower than most other alloys, and it has very good oxidation resistance up to 1500°F (815°C). Other notable characteristics include excellent low cycle fatigue properties and resistance to high-temperature fluorine rich environments.

**Applications include:** Seal rings, Containment rings, Duct segments, Casings, Fasteners, Nozzles, Pumps, Fluoroelastomer process equipment, HF acid processing equipment, Springs

Industries supplied include: Aerospace, Industrial Heat Treating, Power Generation, Chemical Processing

Nominal Composition														
	С	Mn	Si	Р	S	В	Ni	Cr	Со	Мо	La	W	Al	Fe
min	0.05	0.30	0.25	-	-	-	Bal	20.00	-	1.00	0.005	13.00	-	-
max	0.15	1.00	0.75	0.030	0.015	0.015	-	24.00	5.00	3.00	0.05	15.00	0.50	3.00

**Physical Properties** 

	At 70°F	At 20°C
Density	0.327 lb/in <sup>3</sup>	9.05 g/cm <sup>3</sup>
Modulus of Elasticity (E)	33.2 x 10 <sup>3</sup> ksi	229 GPa
Coefficient of Expansion	8.3 μin/in-°F (70-1800°F)	15.0 μm/m-°C (25-1000°C)
Electrical Resistivity	48.0 μohm-in	122.0 μohm-cm
Thermal Conductivity	75.7 Btu-in/ft²-hr-°F	11.3 W/m-°C

#### **Typical Mechanical Properties**

Condition	Heat Treatment	Tensile Strength	Suggested Operating Conditions		
Annealed	1900-2050°F (1040-1120°C)	110-140 ksi (758-965 MPa)	Up to 1500°F (815°C)		
Aged	1200°F (650°C) 24-48 hours	170 ksi min (1172 MPa)	Up to 1200°F (650°C)		

Haynes® 242® is a registered trademark of Haynes International, Inc.

Limitation of Liability and Disclaimer of Warranty:

- The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.
- Applications may be discussed, however, Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., does not recommend or endorse any material for any particular end use or application.
- The data included in this data sheet are typical values and may vary.
- Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.
- In no event will Elgiloy Specialty Metals, a Division of Combined Metals of Chicago L.L.C., be liable for any damages whatsoever arising from the use of the information included in the data sheets.

For further information: Email: wireinquiries@elgiloy.com Phone: 1-847-695-1900 Elgiloy Specialty Metals – Wire Products 356 North Cross Street Sycamore, IL 60178 USA

www.elgiloy.com