

Combined Metals Company, LLC Data Sheet

Alloy 301 Stainless Steel

**UNS: S30100
EN-DIN: 1.4310**

Austenitic chromium-nickel stainless steel. Its high strength and corrosion resistance makes it versatile alloy for a wide variety of applications. Typical applications include appliances, automotive applications, utensils, and high strength structural parts.

Nominal Composition

	C	Mn	P	S	Si	Cr	Ni	N	Fe		
min	-	-	-	-	-	16.0	6.0	-	-		
max	0.15	2.0	0.045	0.030	1.00	18.0	8.0	0.10	BAL		

Physical Properties

	At 70°F	At 20°C
Density	0.285 lb./in ³	7.88 g/cm ³
Modulus of Elasticity (E)	28.0 x 10 ³ ksi	193 x 10 ³ MPa
Coefficient of Expansion	9.4 x 10 ⁻⁶ microinches/in.-°F (70-600°F)	16.9 μm/m-°C (20-300°C)
Electrical Resistivity	27.4 μ ohm.in	69.5 μ ohm.cm
Thermal Conductivity	9.4 Btu-in./ft. ² hr.-°F	16.2 W/m-K

Applicable Specifications

ASTM A240, ASTM A666

Typical Mechanical Properties – Typical Room Temperature Mechanical Properties

Condition	Tensile Strength Min (UTS)	0.2% YS Min	Elongation% in 2" Min (50.8 mm)	Hardness Rockwell
Annealed (Min)	75 ksi (515 MPa)	30 ksi (205 MPa)	40%	95 HRBW (Max)

Typical mechanical properties are based on ASTM A240

Tempered Properties available upon request

For further information:

WWW.COMBMET.COM

Call: (800) 323-0758

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Combined Metals Company, LLC, does not recommend or endorse any material for any particular end use or application.

In no event will Combined Metals Company, LLC, be liable for any damages whatsoever arising from the use of the information included in the data sheets.

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Combined Metals Company, LLC, does not recommend or endorse any material for any particular end use or application.