



Combined Metals Company, LLC

Data Sheet

Alloy 304L Stainless Steel

UNS: S30403
EN-DIN: 1.4306

Industries supplied include: Process equipment in mining, chemical, cryogenic, food, dairy, and pharmaceutical industries. 304 grade stainless has excellent welding and formability characteristics and is one of the most utilized stainless steels. 304L is an extra low carbon grade with a 0.03% max carbon content that eliminates carbide precipitation due to welding.

Nominal Composition

	C	Mn	P	S	Si	Cr	Ni	N	Fe		
min	-	-	-	-	-	17.5	8.0	-	-		
max	0.030	2.0	0.045	0.030	0.75	19.5	12.0	0.10	BAL		

Physical Properties

	At 70°F	At 20°C
Density	0.29 lb./in ³	8.03 g/cm ³
Modulus of Elasticity (E)	28.0 x 10 ³ ksi	193 x 10 ³ MPa
Coefficient of Expansion	9.4 x 10 ⁻⁶ microinches/in.-°F (70-600°F)	16.9 μm/m-°C (20-300°C)
Electrical Resistivity	28.4 μ ohm.in	72 μ ohm.cm
Thermal Conductivity	9.4 Btu-in./ft. ² hr.-°F	16.2 W/m-K

Applicable Specifications

AMS 5513, ASTM A313, ASTM A240, ASTM A580, ASTM A 666, AMS 5511

Typical Mechanical Properties – Typical Room Temperature Mechanical Properties

Condition	Tensile Strength Min (UTS)	0.2% YS Min	Elongation% in 2" Min (50.8 mm)	Hardness Rockwell
Annealed (Min)	70 ksi (485 MPa)	25 ksi (170 MPa)	40%	92 HRBW (Max)

Typical mechanical properties are based on ASTM A240

Tempered Properties available upon request

For further information:
WWW.COMBMET.COM
Call: (800) 323-0758

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Combined Metals Company, LLC, does not recommend or endorse any material for any particular end use or application.

In no event will Combined Metals Company, LLC, be liable for any damages whatsoever arising from the use of the information included in the data sheets.

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Combined Metals Company, LLC, does not recommend or endorse any material for any particular end use or application.