



Combined Metals Company, LLC

Data Sheet

Alloy 434 Stainless Steel	UNS: S43400 EN DIN: 1.4113
----------------------------------	---

Description: Type 434 is a modification of Type 430, and one of the most widely used “non-hardenable” ferritic stainless steels. The addition of molybdenum increases this alloy’s corrosion resistance and its attack from many de-icing chemicals. It also provides good heat and oxidation resistance up to 1500 °F as well as good mechanical properties. Heating above the critical austenite forming temperature leads to a room temperature microstructure of ferrite and fine martensite. As-annealed the alloy is ferritic. Maximum service temperature is 1500 °F.

Applications include: Automotive trim, appliances, combustion chambers, architectural

Industries supplied include: Automotive, Oil & Gas, Food Processing

Nominal Composition

	C	Mn	P	S	Si	Cr	Mo	Fe
min	-	-	-	-	-	16.0	0.75	BAL
max	.12	1.0	0.04	0.030	1.00	18.0	1.25	-

Physical Properties

	At 70°F	At 20°C
Density	0.28 lb/in ³	7.74 g/cm ³
Modulus of Elasticity (E)	28.0 x 10 ³ ksi	193 GPa
Coefficient of Expansion	5.8 µin/in-°F (32-212°F)	10.4 µm/m-°C (0-100°C)
Electrical Resistivity	23.68 µohm-in	60 µohm-cm
Thermal Conductivity	15.1 Btu-in/ft ² -hr- °F (212°F)	26.1 W/m-K (100°C)

Applicable Specifications

Strip & Sheet	ASTM A240
---------------	-----------

Typical Mechanical Properties Typical Room Temperature Mechanical Properties

Condition	Tensile Strength (UTS)	0.2% Offset Yield	Elongation in 2" (50.8 mm)	Hardness Rockwell
Annealed	80 ksi (655 MPa)	50 ksi (290 MPa)	28%	75 HRBW

Typical mechanical properties are based on ASTM A240

For further information:

(800) 323-0758

WWW.COMBMET.COM

LIMITATION OF LIABILITY AND DISCLAIMER OF WARRANTY:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Combined Metals Company, LLC, does not recommend or endorse any material for any particular end use or application.

In no event will Combined Metals Company, LLC, be liable for any damages whatsoever arising from the use of the information included in the data sheets.

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed, however, Combined Metals Company, LLC, does not recommend or endorse any material for any particular end use or application.